

# TITLE OF THE INVENTION

*a* Method of Manufacturing an Annular Member Made <sup>from</sup> of a Metal Sheet Having a Peripheral Wall

## 5 BACKGROUND OF THE INVENTION

### 1. Field of the Invention

*a* The present invention relates to a method of manufacturing an annular member made <sup>from</sup> of a metal sheet used for a pulley or *a* 10 the like, particularly, an annular member made <sup>from</sup> of a metal sheet having a peripheral wall, the peripheral wall has a shape of protruding to either side of a plate-like base portion surrounded by the peripheral wall.

### 15 2. Description of the Prior Art

*a* A conventional method of manufacturing this kind of annular member made <sup>from</sup> of a metal sheet, is schematically shown in Figs. 13 to 15. According to the manufacturing method, a disc-shaped material 1 made <sup>from</sup> of the metal sheet, having a predetermined *a* 20 thickness T3 shown in Fig. 13, is employed thereby manufacturing the member. In other words, the material 1 is held between a pair of dies, not shown in <sup>the</sup> Figures, thereby rotating the material 1 with the dies, while, against an axial center portion of an outer periphery of the material 1 as shown in Fig. 14, a roller *a* 25 2 for splitting the outer periphery of the material is pressed

to split the outer periphery of the material in a forked state,  
 thereby forming a splitting portion 3. As shown in Fig. 15,  
 against the splitting portion 3, a forming roller 4 is pressed,  
 thus forming a peripheral wall 6 protruded on both sides of a  
 non-processed portion 5.

*According*  
 However, according to the conventional manufacturing  
 method described in Figs. 13 to 15, the outer periphery of the  
 material 1 is split, thereby forming the splitting portion 3  
 which is axially extended to form the peripheral wall 6. As  
 a result, a thickness T3 of the disc-shaped material 1 made of  
 the metal sheet is required to be at least 2 or more times *the*  
 thickness required to *make* the peripheral wall 6. In other words,  
 it is required to employ the thick material 1 before forming  
 the peripheral wall 6 of the determined thickness T4, and the  
 thickness T3 of the non-processed portion 5 has the same  
 measurements as the thickness T3 of the original material 1  
 whereby there is a problem wherein it is difficult to achieve  
 a produced annular member *light weight* having a light weight.

Moreover, it is difficult *for the* that a thickness T4 of the  
 peripheral wall 6 *to be* is finished so as to be larger than the  
 thickness T3 of the non-processed portion 5. In order to finish  
 it as mentioned above, there has been a problem wherein a  
 thickness disposal of the peripheral wall in a post step must  
 be additionally conducted.

## SUMMARY OF THE INVENTION

*a* The present invention <sup>*addresses*</sup> ~~has been conducted in view of~~ the above mentioned problems and circumstances. According to the present invention, a thin disc-shaped material made of a metal sheet is employed to make it possible to form a peripheral wall.

*a* Accordingly, <sup>*an*</sup> ~~the~~ object of the present invention is to provide <sup>*for*</sup> a manufacturing method of the annular member made of a metal sheet, having the peripheral wall, easily leading to <sup>*a light weight*</sup> ~~the~~ annular member <sup>*being*</sup> ~~to be produced being~~ lightweight.

*a* In addition, another object of the present invention is to provide a manufacturing method <sup>*for*</sup> of an annular member made of a metal sheet, having a peripheral wall, which can make the peripheral wall thinner or thicker than a non-processed portion.

*a* 15 A method of manufacturing an annular member made <sup>*from*</sup> ~~of~~ a metal sheet having a peripheral wall according to the present invention, comprises the steps of:

*a* 20 rotating a disc-shaped material made of a metal sheet, pressing an outer periphery of the material in a radially inward direction, while <sup>*metal sheet*</sup> ~~rotating~~ <sup>*metal sheet*</sup> ~~the~~ material, <sup>*continuing to rotate*</sup>

*a* thickening the outer periphery axially by pressing it, <sup>*the*</sup> protruding the outer periphery to either side of <sup>*metal sheet*</sup> ~~the~~ non-processed portion of the material, and

*a* 25 forming a peripheral wall protruding to ~~the~~ either side of the non-processed portion.

007260-8725760

The present invention is not a method wherein an outer  
 periphery of the <sup>metal sheet</sup> material is split before it is developed,  
 thereby forming the peripheral wall, but a method wherein the  
 outer periphery thereof is axially thickened while extending  
 it to the both sides of the non-processed portion of the <sup>metal sheet</sup> material,  
 thus forming the peripheral wall. Accordingly, even if the  
 material is too thin to be split, the outer periphery of the  
 material can be formed as a peripheral wall protruded to the  
 both sides of the non-processed portion. Additionally, there  
 is formed a peripheral wall having a thickness corresponding  
 to a radial width of the outer periphery of the <sup>metal sheet</sup> material formed  
 as the peripheral wall. Consequently, a width thereof is  
 appropriately predetermined, thereby easily making it possible  
 to make the peripheral wall thicker or thinner. As a result,  
 it is also possible to thicken the peripheral wall more than  
 the non-processed portion.

According to the present invention, in an intermediate  
 phase of the step of thickening the outer periphery of the  
 material axially, a preliminary peripheral wall may be formed  
 so that the outer periphery thereof may have an axial center  
 portion which is more outwardly protrusive than <sup>both</sup> axial ~~both~~ ends,  
 in an arc-shaped state. Thus, the outer periphery of the  
 material is formed as the preliminary peripheral wall shaped  
 as mentioned above, before forming it as the peripheral wall  
 protruding to the both of the non-processed portion. As a

result, all steps from an initial forming step to a finishing step of finishing the outer periphery of the <sup>metal sheet</sup> material into the peripheral wall thereof can be unforcedly conducted.

Moreover, according to the present invention, in advance of forming the preliminary peripheral wall, the outer periphery of the <sup>metal sheet</sup> material may be formed so that a sectional face thereof may have a substantially circular shape. Thus, the outer periphery of the <sup>metal sheet</sup> material is formed so that the sectional face thereof may have a substantially circular shape, before it is formed as the preliminary peripheral wall having the above shape. Thereafter, the peripheral wall protruding to ~~the~~ both sides of the non-processed portion is formed by stages, thereby enabling the steps from the initial forming step to the finishing step of finishing the outer periphery thereof into the peripheral wall thereof to be further unforcedly conducted. Herein, the above expression of "a sectional face thereof may have a substantially circular shape" includes cases wherein a sectional shape is an exact circle, a shell-shaped circle, and a distorted circle.

Moreover, preferably, the present invention adopts a method comprising the steps of:

holding the non-processed portion of the <sup>metal sheet</sup> material between a pair of dies,  
rotating the <sup>metal sheet</sup> material with the dies,  
pressing a forming surface of a forming roller against

the outer periphery of the <sup>metal sheet</sup> material, and

rotating the forming roller together with the <sup>metal sheet</sup> material.

In this case, the steps of forming the annular member having

the peripheral wall ~~of the~~ disc-shaped <sup>metal sheet</sup> material made ~~of the~~

~~metal sheet~~ can be unforcedly conducted.

Furthermore, preferably, the present invention includes a finishing step of finishing the preliminary peripheral wall protruding to either side of the non-processed portion, in a predetermined shape.

In case of adopting the manufacturing method, the preliminary peripheral wall can be finished so as to lead to the peripheral wall having an optional shape. As a result, for example, the outer peripheral surface of the peripheral wall can be finished so as to be axially flat or axially curved in an arc-shape, or a flange can ~~be~~ protruded to <sup>both</sup> axial ~~both~~ ends of the peripheral wall, or a poly-V-groove can be formed on the outer peripheral surface of the peripheral wall.

Other features and effects of the present invention are further clarified by embodiments described ~~as~~ below.

#### BRIEF DESCRIPTION OF THE DRAWINGS

Figs. 1A and 1B are diagrams ~~of a chevron portion forming step of forming~~ a chevron portion.

Figs. 2A and 2B are diagrams ~~of a substantially circular portion forming step of forming~~ a substantially circular

portion.

Figs. 3A and 3B are diagrams of ~~a preliminary peripheral wall forming step of forming~~ a preliminary peripheral wall.

5 Figs. 4A and 4B are diagrams of ~~a rough peripheral wall forming step of forming~~ a rough wall.

Figs. 5A and 5B are diagrams of ~~a peripheral wall forming step of forming~~ a peripheral wall (i.e., a finishing step).

Fig. 6 is an enlarged sectional view of the chevron portion.

10 Fig. 7 is an enlarged sectional view of the substantially circular portion.

Fig. 8 is an enlarged sectional view of the preliminary peripheral wall.

15 Fig. 9 is an enlarged sectional view of the rough peripheral wall.

Fig. 10 is an enlarged sectional view of the peripheral wall.

Fig. 11 is an enlarged sectional view of a peripheral wall according to a modification.

20 Fig. 12 is an enlarged sectional view of a peripheral wall according to another modification.

Fig. 13 is a partially sectional view of a <sup>metal sheet</sup> material employed in a conventional method.

25 <sup>metal sheet</sup> Fig. 14 is a diagram of a slitting step of slitting the material, according to the conventional method.

05157318-0921590

*a*  
~~Fig. 15 is a diagram of a peripheral wall forming step.~~  
~~of forming a peripheral wall according to the conventional~~  
~~method.~~

## 5 DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

*a*  
 Referring now to the drawing, a preferred embodiment of the <sup>present</sup> invention is described below.

*a*  
 Figs. 1 to 5 are diagrams showing each step of the embodiment of a manufacturing method according to the present invention.

Figs. 6 to 10 are diagrams showing a section of the outer periphery of the <sup>metal sheet</sup> material formed by ~~the~~ each step.

*a*  
 In this embodiment, a disc-shaped material 10 made of metal sheet is previously subject to a drawing process, whereby as shown in Fig. 1A, a swelling portion 11 having a circular shape and a flange portion 12 around it are concentrically disposed. A center of the swelling portion 11 having the circular shape is provided with a round hole 13 formed by piercing. The round hole 13 can be employed as a fixing hole for fixing it <sup>on</sup> a shaft of a rotary rod or the like.

*a*  
*a*  
*a* *C*  
*B* *C*  
*C*  
 As shown in Fig. 1A, in the disk-shaped material 10 made of a metal sheet, <sup>the</sup> inner portion between the swelling portion 11 and the flange portion 12 is <sup>referred to</sup> decided as a non-processed portion 14. A process for forming a peripheral wall 21 (see Fig. 5B) is applied to an outer periphery 15 of an outside of

C the non-processed portion <sup>1</sup>14. A radial width of the outer periphery 15 is appropriately predetermined, taking an axial length and a thickness of the peripheral wall 21 (see Fig. 5B) to be formed into consideration.

5 As shown in Fig. 1A, the non-processed portion <sup>1</sup>14 of the <sup>metal sheet</sup> material 10 is held between a pair of dies or an upper die 100 and a lower die 200, and the dies 100, 200 are rotated, thereby rotating the <sup>metal sheet</sup> material 10 with the dies 100 and 200. The dies 100 and 200 are employed in common through all steps shown in 10 Figs. 1 to 5. Additionally, a shape and a thickness T1 of the non-processed portion <sup>1</sup>14 of the <sup>metal sheet</sup> material 10 are not substantially changed by conducting the whole steps.

As shown in Fig. 1A, a first forming roller 300 is disposed to be opposed to the outer periphery 15 of the <sup>metal sheet</sup> material 10 held 15 between the pair of dies 100, 200. A valley-shaped forming surface 310 expanded outwardly and included in the first forming roller 300 is moved <sup>radially from</sup> from a radial outside to the outer periphery 15. As shown <sup>by</sup> in an arrow "a" in Fig. 1B, the first forming roller 300 is advanced, thereby pressing the outer periphery 15 of the <sup>metal sheet</sup> material 10 in a radially inward direction by means of the valley-shaped forming surface 310 (see Fig. 1A). Thereafter, 20 the first forming roller 300 is rotated together with the <sup>metal sheet</sup> material 10, the outer periphery 15 is radially reduced in rotation while it is axially thickened with the result that <sup>1</sup> 25 shape having the same shaped outline as the valley-shaped

09157318-09199

forming surface 310 is formed. Namely, a sectional chevron shape having a round top as enlarged and shown in Fig. 6 is formed. A chevron portion 16 having such a shape is annularly disposed around it so as to extend to either side of the non-processed portion ~~14~~. <sup>1, or flange portion 12 shown in Fig. 6</sup>

In a next step, as shown in Fig. 2A, a second forming roller 400 is disposed to be opposed to the chevron portion 16. A semi-circular forming surface 410 disposed on the second forming roller 400 is moved from ~~a radial~~ <sup>radially</sup> outside to the chevron portion 16. As shown <sup>by</sup> in an arrow "b" in Fig. 2B, the second forming roller 400 is advanced, thereby pressing the chevron portion 16 (see Fig. 2A) in a radially inward direction, on the semi-circular forming surface 410. Thereafter, the second forming roller 400 is rotated together therewith, whereby the chevron portion 16 is radially reduced in rotation while it is axially thickened, a shape having the same shaped outline as the semi-circular forming surface 410 is formed so that a sectional face thereof may have a substantially circular shape as enlarged and shown in Fig. 7. The substantially circular portion ~~16~~ <sup>17</sup> formed as mentioned above is annularly disposed around the non-processed portion ~~14~~ so as to protrude to ~~the~~ both sides of the non-processed portion ~~14~~. The section of the substantially circular portion 16 may be exactly circular or shell-shaped though the shape of the substantially circular portion ~~16~~ <sup>17</sup> in Fig. 7 is distorted.

09157313-092199

In a next step, as shown in Fig. 3A, a third forming roller 500 is disposed so as to be opposed to a substantially circular portion 17, a shallow concave forming surface 510 included in the third forming roller 500 is moved from a <sup>radially</sup> radial outside to the substantially circular portion 17. As shown <sup>by</sup> in an arrow "c" in Fig. 3B, the third forming roller 500 is advanced, the substantially circular portion 17 (see Fig. 3A) is pressed to a radially inward direction, by means of the concave forming surface 510, the third forming roller 500 is rotated together, the substantially circular portion 17 is radially reduced in rotation while it is axially thickened, with the result that a shape having the same shaped outline as the concave forming surface 510 is formed as a sectional preliminary peripheral wall 18 as enlarged and shown in Fig. 8. The preliminary peripheral wall 18 having such a shape is annularly disposed around it so as to extend to either side of the <sup>Flanged portion 12 of the</sup> non-processed portion 14. The preliminary peripheral wall 18 as illustrated in Fig. <sup>8</sup> 3A, is provided with flat portions 18a, 18a on the both ends in an axial direction, a swelling portion 18b having a small height is disposed on an axial central portion, which is situated more outwardly than the flat portions 18a, 18a, and the swelling portion 18b has a great curvature so as to swell in an arc-shape. The outer peripheral surface of the each flat portion 18a and the outer peripheral surface of the swelling portion 18b are smoothly continuous.

00157318-092198

In a next step, as shown in Fig. 4A, a fourth forming roller 600 is disposed to be opposed to the preliminary peripheral wall 18, a groove-shaped forming surface 610 included in the fourth forming roller 600, whose bottom surface is flat and shallow, is moved from ~~a radial~~ <sup>radially</sup> outside to the preliminary peripheral wall 18. As shown <sup>by</sup> in an arrow "d" in Fig. 4B, the fourth forming roller 600 is advanced, the preliminary peripheral wall 18 (see Fig. 4A) is pressed <sup>in</sup> ~~to~~ a radially inward direction on the groove-shaped forming surface 610, thereby rotating the fourth forming roller 600 therewith, and mainly the swelling portion 18b (see Fig. 8) of the preliminary peripheral wall 18 is radially reduced in rotation, while, a whole of the preliminary peripheral wall 18 is slightly axially thickened. Consequently, a shape having the same shaped outline as the groove-shaped forming surface 610 is formed as a sectional rough peripheral wall 19 as enlarged and shown in Fig. 9, the rough peripheral wall portion 19 having such a shape is annularly disposed around it so as to extend to either side of the non-processed portion ~~14~~. As illustrated in the figure, the rough peripheral wall 19 is not yet well-finished because the shape of the end surfaces 19a, 19a of the axial both ends is rounded.

In a next step, as shown in Fig. 5A, a fifth forming roller 700 is disposed so as to be opposed to the rough peripheral wall 19, a groove-shaped forming surface 710 included in the fifth

05157318-092199  
 991260-8725750

forming roller 700, whose bottom surface is flat and shallow,  
 is moved from <sup>radially</sup> ~~the radial~~ outside to the preliminary peripheral  
 wall 19. The groove-shaped forming surface 710 has a shape  
 enabling the end surfaces 19a, 19a of the rough peripheral wall  
 19 shown in Fig. 9 to be finished accurately, for example, a  
 shape enabling the end surfaces 19a, 19a to be exactly shaped.  
 As shown <sup>by</sup> ~~in~~ an arrow "e" in Fig. 5B, the fifth forming roller  
 700 is advanced, the rough peripheral wall 19 (see Fig. 5A) is  
 pressed in a radially inward direction on the groove-shaped  
 forming surface 710, the fifth forming roller 700 is rotated  
 together therewith, mainly the end surfaces 19a, 19a of the  
 axial both edges of the rough peripheral wall 19 are formed in  
 rotation so as to make a right angle with the outer peripheral  
 surface, which are formed as the peripheral wall 21 having the  
 same shaped outline as the groove-shaped forming surface 710.  
 The peripheral wall 21 formed in such a manner, is annularly  
 disposed around it, so as to protrude to ~~the~~ either side of the  
 non-processed portion <sup>14</sup>. The peripheral wall 21 formed in this  
 manner has ~~the~~ both end surfaces which are exactly shaped as  
 enlarged and shown in Fig. 10. The peripheral wall 21 is equally  
 protruded to either side of the non-processed portion <sup>14</sup>. The  
 outer peripheral surface thereof is axially flat. A thickness  
 T2 and an axial length of the peripheral wall 21 shown in Fig.  
 10 have each size fitted in a radial width of the outer periphery  
 15 of the original material 10.

09157318-092193

According to the manufacturing method mentioned above, the rough peripheral wall 19 formed in the step of Fig. 4B, is finished by the finishing step of Fig. 5B, leading to the peripheral wall 21 having ~~a~~ high accuracy. Before the preliminary peripheral wall 18 formed in the step of Fig. 3B is finished leading to the peripheral wall 21, a step of forming the rough peripheral wall 19 is interposed. Also, the finishing step may be conducted immediately after the preliminary peripheral wall 18 is formed, thereby forming the peripheral wall 21. As the case may be, after a state wherein the non-processed portion ~~14~~ of the material 10 as shown in Fig. 1A is held between the pair of dies 100, 200, a step wherein the preliminary peripheral wall 18 is directly formed on the outer periphery 15 may be conducted. Alternatively, a step of forming directly the substantially circular portion 17 and a step of forming a preliminary peripheral wall 18 may be subsequently conducted. Additionally, there is also a case wherein a step of forming directly the peripheral wall 21 is conducted.

In the finishing step mentioned above, the peripheral wall 21 having ~~the~~ axial both end surfaces which are exactly shaped, is formed. However, the shape of the forming surface of the forming roller is changed, whereby it is also possible to form the peripheral wall 21 having the outer peripheral surface extended in an arc shape as shown in Fig. 11, or form

00153310-00153310

the peripheral wall 21 including the flanges 22, 22 protruded outwardly on the both ends in the axial direction as shown in Fig. 12.

The annular member having the sectional-shaped peripheral wall 21 shown in Figs. 10, 11 and 12 can be employed as a back side pulley for winding a flat belt. Moreover, though it is not shown in figures, a poly-V-groove may be disposed on the outer peripheral surface of the peripheral wall 21 in the finishing step. The annular member manufactured in such a way, may be employed as the poly-V-groove pulley for winding the poly-V-belt.

As mentioned above, not only in <sup>the</sup> case that the disc-shaped material made of the metal sheet is originally thick, but also in <sup>the</sup> case that the material is too thin to be split, the above manufacturing method makes it possible to form a peripheral wall having a necessary thickness, thereby having <sup>the</sup> effect of facilitating the ~~produced~~ <sup>the</sup> annular member ~~to be lightweight.~~ Moreover, regardless of the thickness of the non-processed portion, a remarkable effect of enabling the peripheral wall to be formed in a state of a desirable thickness can be achieved. Therefore, a back surface pulley for supporting a back surface of a belt, a pulley with a flange, a pole piece V-groove pulley or the like having light weight can be easily manufactured.

~~The entire disclosure of Japanese Patent Application No.~~

~~9-272676 filed on October 6, 1997 including specification,~~

09157318-092198  
092260-092198

in a

a

a

*a* ~~claims, drawings and summary are incorporated herein by~~  
*a* ~~reference in its entirety.~~

5

10

15

20

25

09157318-092198  
867260-87E/5T60